

产品类别 Product Category	牌号Grade	测试标准、测试项目 Test criteria, test items							特性及用途 Property and Application
		熔指 MFI g/10min	拉伸强度 Tensile Strength MPa	弯曲强度 Flexural Strength Mpa	弯曲模量 Flexural modulus Mpa	悬臂梁缺口冲击强度 Notched Izod impact strength J/m	热变形温度HDT (1.82MPa) °C	阻燃性 Flame retardance	
		ASTM D1238	ASTM D638	ASTM D790		ASTM D256	ASTM D648	UL 94	
无卤阻燃 PC/ABS Halo-free flame retarded PC/ABS	NH-9012	15, 260°C, 2.16kg	59	91	2500	650	115	1.5mmV0 3.0mm5VA	阻燃高耐热, 路由器外壳 High flame retardancy,heat resistance, router shell
	NH-9012HF	30, 260°C, 2.16kg	60	90	2380	550	101	1.5mm V0	高阻燃高流动, TV显示器 High flame retardancy and high flow, TV display
玻纤增强 PC/ABS Glass fibre reinforced PC/ABS	NH-9018G10	20, 260°C, 2.16kg	75	115	4500	80	97	1.5mm V0	阻燃低浮纤, TV前框后壳 Flame retardancy low floating fiber, TV front frame back coverl
	NH-9018G15	30, 260°C, 2.16kg	80	120	4800	60	98	1.5mm V0	阻燃低翘曲, 音响外壳 Flame retardancy low warping, stereo shell
矿纤增强 PC/ABS Mineral-fibre reinforced PC/ABS	NH-9016M05	15, 260°C, 2.16kg	62	93	3200	450	92	1.0mmV0	矿纤增强, 笔记本胶框 Mineral fiber reinforcement, Laptop plastic frame
	NH-9016M15	13, 260°C, 2.16kg	65	96	4850	80	98	1.5mmV0	矿纤增强, 笔记本外壳 Mineral fiber reinforced, Laptop cover
	NH-9016M20	28, 260°C, 2.16kg	60	90	4500	35	88	1.5mmV0	矿纤增强, TV显示器 Mineral fiber reinforced, TV display
车用 PC/ABS AUTO PC/ABS	CR-9004Y	12, 260°C, 2.16kg	58	80	2200	650	125	HB	耐热高冲击, 汽车内外饰 Heat resistant high impact, automotive interior and exterior trim
	CR-9004EP	10, 260°C, 2.16kg	56	72	2000	350	105	HB	高强度易喷涂, 汽车外饰 High strength easy to spray, Automotive exteriors
PC/ASA合金 PC/ASA alloy	CR-9005	15, 260°C, 2.16kg	60	78	2100	500	120	HB	高强度超耐候, 汽车天窗 High strength super weather-proof, car sunroof